



PROCOP
— 1802

SOPORSET PREMIUM OFFSET



		60 g/m	70 g/m	75 g/m	80 g/m	90 g/m	100 g/m	110 g/m	120 g/m
OFFSET	Whiteness CIE	ISO 11475	161	161	161	161	161	161	161
	Opacity %	ISO 2471	87	91	92	94	95	96	98
	Moisture %	ISO 287	6,2	6,2	6,2	6,0	6,0	6,0	5,8
	Bendtsen Roughness ml/min	ISO 879/2	150	150	180	150	150	150	150
	Thickness µm	ISO 534	80	92	95	106	116	128	141
	Bulk µm/g/m²	-	1,33	1,31	1,27	1,33	1,29	1,28	1,25
	Certi fied	FSC ⁽¹⁾	✓	✓	✓	✓	✓	✓	✓
	Awarded by	Eco-label ⁽²⁾	✓	✓	✓	✓	✓	✓	✓

		135 g/m²	150 g/m²	170 g/m²	190 g/m²	225 g/m²	250 g/m²	300 g/m²	350 g/m²
OFFSET	Whiteness CIE	ISO 11475	161	161	161	161	161	161	161
	Opacity %	ISO 2471	≥98	≥98	≥99	≥100	≥100	≥100	≥100
	Moisture %	ISO 287	6,5	6,5	6,5	6,5	6,5	6,5	6,5
	Bendtsen Roughness ml/min	ISO 879/2	150	150	180	180	180	180	200
	Thickness µm	ISO 534	158	176	200	224	265	295	354
	Bulk µm/g/m²	-	1,17	1,17	1,18	1,18	1,18	1,18	1,18
	Certi fied	FSC ⁽¹⁾	✓	✓	✓	✓	✓	✓	✓
	Awarded by	Eco-label ⁽²⁾	✓	✓	✓	✓	✓	✓	✓

