



PROCOP
— 1802

SOPORSET PREPRINT



		75g/m ²	80g/m ²	90g/m ²	100g/m ²	120g/m ²	135g/m ²	160g/m ²	250g/m ²	300g/m ²
PRE-PRINT	Whiteness CIE	ISO 11475	169	169	169	169	169	169	169	169
	Opacity %	ISO 2471	93	95	96	97	98	≥98	≥99	≥100
	Moisture %	ISO 287	5.0	5.0	5.0	5.2	5.2	5,4	5,4	5,4
	Bendtsen Roughness ml/min	ISO 879/2	180	150	150	100	150	150	150	150
	Thickness μm	ISO 534	103	108	114	118	125	158	187	293
	Bulk μm/g/m ²	-	1,37	1,35	1,27	1,18	1,04	1,17	1,17	1,17
	Certi fied	FSC ⁽¹⁾	✓	✓	✓	✓	✓	✓	✓	✓
	Awarded by	Eco-label ⁽²⁾	✓	✓	✓	✓	✓	✓	✓	✓

